



**SEAL-FLEX® LR-6
3/8 Inch Latex Mat System**

PRODUCT SPECIFICATIONS

DESCRIPTION:

SEAL-FLEX® LR-6 latex bound layered type surfacing 3/8" thick in the color black as manufactured by the SEAL-FLEX™ Corporation. The original patented (#4,474,833) rake and spray process and the SEAL-FLEX™ surface have been chosen because of the proven superior durability for more than twenty (20) years. SEAL-FLEX™ must be installed over a properly laid asphalt or concrete substrate (minimum cross slope of 1.0 %). The surface is available in black. (red, blue, and green are available but there will be an additional cost.)

PRODUCTS BY WEIGHT:

| | |
|--------------------------------|------------------|
| Base Rubber - | 6.50 lbs / sq yd |
| Surface Rubber - | 2.00 lbs / sq yd |
| Latex Binder - 50% Solids..... | 0.85 gal / sq yd |
| Latex Primer..... | 0.05 gal / sq yd |

APPLICATION:

- 1) Prime coat of latex applied at 0.05 gallons per square yard.
- 2) Rubber applied and over-sprayed with 0.1 gallons of latex per square yard.
- 3) Multiple layers of rubber and latex shall be applied until proper thickness is achieved.
- 4) A final coating of latex with a UV Inhibitor shall be applied.
- 5) Apply lines and event markings.

Before application of the synthetic surface can begin, the asphalt should be cured for at least 14 -21 days, and a concrete base a minimum of 28 days.

All material is to be prime grade with no off specification materials allowed. Each layer in the installation shall be applied in a thorough, workmanlike manner, and each layer shall be cured before beginning the next layer. No work shall be done in temperatures below 40 degrees or in the rain.

Products are disclosed by weight or volume. Actual product coverage rates will vary depending on site conditions.



STRIPING:

An individual experienced in track striping must do all work. The event markings shall conform to the rules and regulations of either the National Federation of State High School Associations or the National Collegiate Athletic Association whichever is applicable.

MANUFACTURER:

SEAL-FLEX LR-6 is manufactured by: Hellas Sport Surfaces a Division of Hellas Const., Inc.

Hellas Construction Inc.
12710 Research Blvd. Ste. 240
Austin, Texas 78759
T 512.250.2910
F 512.250.1960
www.hellasconstruction.com

At the Top of the Game™